RG104 E-1 Box 121

WEEKLY REPORT OF GOLD DEPOSITS MELTED AT UNITED STATES MINT.

1880

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.		Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner. 17/3/80.	
March	8th	1439 G. C. Thompson	11	39	11	23		16	1	45			Bar & Button	The deposits are from the	
		40 S. Rosenbaum	19	93	17	34	2	59	12	95			Jewelry & Watch Cases	following sources:	
		1 W. H. Sheafer & Co.	36	10	29	83	6	27	17	42			Buttons, Base	N. Carolina (1)	2
		2 W. H. Lee	87	21	87	17		04		05			Bar	S. Carolina	1
		3 G. C. Thompson	45	23	45	22		01		02			Bar	Georgia (2)	2
		4 A. Bandschopp	15	78	11	68	4	10	25	62			Ring, Base	California (1)	1
		5 Richd Helme	26	86	26	86							U. S. Coin	Finer bullion (4)	7
		6 G. C. Thompson	6	61	6	61							Bar	Jewelry & cases	8
	9th	7 Simons, Bro. & Co.	47	95	47	93		02		04			Bar	Base Bullion	5
		8 Morgan, Hastings & Co.	80	59	80	59							U. S. Coin	Coin	5
		9 Hastings & Co.	80	57	80	57							U. S. Coin	Dental Plate	1
		50 A. London Snowden, Supt.	112	41	112	40		01		009			Bar, U. S. A. O. N. G.	Total	32
		1 Phillips & Jacobs	53	73	53	73							U. S. Coin		
		2 Phil. McDonald	29	82	29	78		04		13			Button, Cal.	The loss in melting the	
	10th	3 G. C. Thompson	15	40	12	88	2	52	16	80			Jewelry, Watch Cases & Rings	finer bullion, 0·19%, is	
		4 do	22	85	18	16	4	19	19	05			Crushed Quartz & Rings	quite low; — in melting	
		5 J. H. Bancroft	20	01	20	00		01		05			Ring, Gen.	jewelry & cases, 12·15%, is	
	11th	6 G. C. Thompson	5	89	5	89							Button, Gen.	full, — in melting very base	
		7 do	22	63	13	73	8	90	38	70			Ring, Base	bullion, 24·71%, is about	
		8 do	20	90	16	84			19	33			Jewelry	a fair average. The loss in	
		9 do	6	86	6	83				43			Button	amalgam from N. Carolina,	
		60 Hastings & Co.	107	47	107	47							U. S. Coin	1·41% is very low, & on that	
	12th	1 Sam. Mackintosh	10	21	10	21							Button	from S. Carolina, 7·19%, is	
	13th	2 G. C. Thompson	37	52	35	20	2	32	6	11			Watch Cases & Jewelry	very full, even excessive.	
		3 do	12	54	10	83	1	71	13	15			Jewelry	The absence of all loss in	
		4 H. Muller's Sons	20	50	20	49		01		05			Bars	melting about 350 oz. of	
		5 S. R. Ford	23	04	20	25	2	79	12	13			Jewelry & Watch Cases	gold coin, in 5 different	
		6 G. C. Thompson	43	83	33	55	9	78	22	34			Buttons, Base	shows excess of care, for it is	
		7 John H. Wall, Cashr	21	08	19	57	1	51	7	19			Aml, S. A.	impossible that there should	
		8 F. H. Leal	15	03	14	61		42	2	80			D'ble & Billings	actually be no loss.	
		9 R. H. Lyon	21	64	21	64	1	00	4	55			Jewelry & Watch Cases	J. P. Booth	
		70 G. H. Smith	15	65	15	34		31	1	94			Aml, N. G.	M. & R.	
			109	623	104	343	52	280	7	29					

Received from U. S. A. O. N. G. during the week and transferred immediately to Melter and Refiner 273,561.17 Oz. in Bars.

For week ending March 13th, 1880

Approximate value, $16,173,16

S. Nobley Dougherty
Register.

To the Director of the Mint.

RG104 E-1 Box 121

Report of Gold Deposits
melted for week ending
March 13th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending March 13, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]